

日期	样品号	化学性能													灼减, %	粒度(+150μ)%	粒度(-45μ)%	粒度
		Al2O3, %	SiO2, %	Fe2O3, %	Na2O, %	ZnO, %	TiO2, %	Ga2O3, %	V2O5, %	CaO, %	K2O, %	Li2O, %	P2O5, %					
	A0240040	98.05	0.007	0.004	0.388	0.0002	0.0025	0.0104	0.0009	0.031	0.024	0	0	0.88	0.4	8.7		
	A0S240313	98.546	0.009	0.001	0.444	0.0003	0.0033	0.0102	0.0009	0.03	0	0	0	0.97	0.5	9.3		
2024年11月13日	A0240641	98.581	0.01	0.002	0.427	0.0007	0.004	0.0104	0.001	0.03	0.002	0	0	0.95	0.4	10.8		
	A0240642	98.573	0.011	0.001	0.444	0.0004	0.0038	0.011	0.0009	0.031	0	0	0	0.94	0.8	9.8		
	A0240643	98.55	0.01	0.002	0.429	0.0007	0.0034	0.0109	0.001	0.029	0	0	0	0.98	0.8	9.5		
2024年11月14日	A0S240315	98.602	0.01	0.003	0.425	0.0009	0.0036	0.011	0.0011	0.03	0.004	0	0	0.93	1.2	8.3		
2024年11月15日	A0240647	98.661	0.01	0.002	0.397	0.001	0.0034	0.0111	0.001	0.03	0.003	0	0	0.9	1	7.8		
	A0240648	98.658	0.01	0.002	0.41	0.0009	0.0033	0.0109	0.0007	0.03	0.004	0	0	0.89	1.1	8.7		
	A0S240316	98.586	0.015	0.002	0.437	0.0009	0.0033	0.0113	0.0011	0.03	0	0	0	0.93	1.1	8.5		
2024年11月16日	A0240649	98.613	0.016	0.001	0.428	0.0004	0.0033	0.0107	0.0009	0.032	0	0	0	0.91	1	9.5		
	A0240650	98.602	0.015	0.002	0.399	0.0006	0.0027	0.0109	0.0009	0.032	0	0	0	0.95	1	9.6		
	A0240651	98.63	0.01	0.002	0.408	0.0005	0.0029	0.0111	0.001	0.03	0	0	0	0.92	1.2	9.8		
	A0S240317	98.581	0.01	0.003	0.406	0.0007	0.0031	0.0109	0.0008	0.03	0.001	0	0	0.97	1.1	8.9		
2024年11月17日	A0240652	98.581	0.011	0.002	0.415	0.0007	0.0031	0.0109	0.001	0.031	0	0	0	0.96	1.1	9.9		
	A0240653	98.642	0.012	0.002	0.414	0.0008	0.0033	0.0114	0.0012	0.03	0	0	0	0.9	1.5	8.5		
	A0240654	98.628	0.011	0.002	0.409	0.0005	0.0032	0.011	0.0009	0.03	0	0	0	0.92	1.4	8.6		
	A0S240318	98.613	0.01	0.003	0.404	0.0007	0.003	0.0109	0.0011	0.03	0.001	0	0	0.94	1.6	5.1		
2024年11月18日	A0240655	98.569	0.009	0.001	0.391	0.0002	0.0028	0.0111	0.0007	0.03	0.0001	0	0	1	1.4	6.6		
	A0240656	98.584	0.01	0.003	0.373	0.001	0.0031	0.011	0.001	0.03	0	0	0	1	0.6	10.3		
	A0S240319	98.631	0.014	0.002	0.403	0.0002	0.003	0.0105	0.0011	0.03	0	0	0	0.92	2	4.3		
2024年11月19日	A0240657	98.666	0.012	0.004	0.377	0.0008	0.0029	0.0111	0.0006	0.031	0	0	0	0.91	1.3	4.7		
	A0240658	98.63	0.011	0.003	0.395	0.0009	0.0031	0.0114	0.0008	0.031	0	0	0	0.93	1.5	5.6		
	A0S240320	98.632	0.01	0.001	0.387	0.0005	0.0037	0.0106	0.0011	0.03	0	0	0	0.94	0.8	8		
2024年11月20日	A0240659	98.642	0.01	0.005	0.403	0.0009	0.003	0.0111	0.0009	0.03	0	0	0	0.91	2	3.7		
	A0240660	0	0	0	0	0	0	0	0	0	0	0	0	1.8				
	A0S240321	0	0	0	0	0	0	0	0	0	0	0	0	1.3				